

Non-Slip Finish

A non-slip finish can be used on all outside concrete surfaces where slippage is a problem, for example ramps, walkways and alfresco areas.

Non-Slip Procedure

- Grind with 30 grit to desired exposure.
- Grind with 60 grit to remove scratches.
- Grind with 120 grit to further remove scratches.
- Thoroughly clean the surface.
- Apply 50/50 coat of sealer.
- Apply one coat of non-slip sealer.
- Apply final coat of sealer.

External Finish

External Finish Procedure

- Grind with 30 grit to desired exposure.
- Grind with 60 grit to remove scratches.
- Grind with 120 grit to further remove scratches if required.
- Thoroughly clean the surface.
- Apply 50/50 coat of sealer.
- Application of at least 2 coats of Sealer.
- Some concrete when ground requires grouting to fill holes and imperfections. This will result in an overall better look, but it is up to the client's discretion.

Maintenance

These finishes are easy to maintain and can be re-applied every 4 to 5 years depending if there is high traffic volume.